

Typical Problems Associated With Patching Compounds?

- ✓ Repairs Require
Special Tools
- ✓ Experienced
Labor Needed
for Application
- ✓ Requires Priming
and Heat for an
Application

APC-II...Performance In Action.

● **EASY-TO-USE.** APC-II is simply spread in the area to be resurfaced and compressed with a hand tamper or roller. It can be applied by the most inexperienced worker.

PERFORMANCE BENEFIT: No priming necessary. No application experience needed. Saves labor, time and money.

● **SETS RAPIDLY.** APC-II will not harden until compressed. Special additives in APC-II enable it to adhere to wet or dry surfaces and also stabilizes the consistency so that it is easy and effective to apply in either sub-freezing or extremely hot temperatures. Resurfaced areas may be opened to traffic immediately after application.

PERFORMANCE BENEFIT: Superior performance. Reduces repair and labor time. Saves money.

● **DURABLE.** APC-II is designed specifically for repair of outdoor asphalt or concrete pavements. APC-II is impervious to water and is unaffected by freezing weather.

PERFORMANCE BENEFIT: Provides maximum protection. Long-lasting patch reduces expensive repeat repairs.



...setting performance
standards worldwide...

APPLICATIONS

APC-II is a bituminous patching material that can be applied directly from the container in any kind of weather. It is self-bonding, requires no heating or mixing and sets by ordinary compression. Used to patch and repair outdoor asphalt and concrete pavements including driveways, walks, parking lots, roads, airports, and loading docks.

DIRECTIONS

Sweep surface to remove loose particles and excessive dust. If the area is extremely dusty, hose it down. It is not necessary to wait for the area to dry before applying the patch. Spread APC-II over the area to be resurfaced, or into the holes to be patched, and compress it with a hand tamper or roller. If the patch is to be applied at a depth exceeding 1 inch, tamp or roll it in layers of 1 inch at a time.

TECHNICAL DATA

Composition:	Bitumen, petroleum distillates
Type:	Asphaltic
Toxicity:	Moderate
Flammability:	Combustible
Drying Time:	None
Coverage:	Approximately 20 sq. ft. per 5 gl. at ½ inch thickness.
Color:	Black
Odor:	Solvent like



...setting performance standards worldwide...

C-4/PC-1062/0205