

Product Data

- **Applies Easily**
- **Sets Up Quickly**
- **Adheres To Most Hard Surfaces**
- **Especially Effective On Surfaces Or Areas Exposed To Weather**
- **Forms A Durable, Long-Lasting Coating**

SLIP-NOT

Slip Resistant Texturized Epoxy Coating

SLIP-NOT is a slip-resistant epoxy coating that cures to a hard, flat, textured finish. It is designed for interior and exterior use on concrete, steel, wood, fiberglass, aluminum, tile, etc. SLIP-NOT is effective anywhere water stands or slippery conditions exist. It contains a synthetic grit with no sharp edges. SLIP-NOT is easy to apply, sets up quickly and is long-lasting.

- ✓ **Improves Safety**
- ✓ **Reduces Slips & Falls**
- ✓ **Reduces Your Risks & Liability**
- ✓ **Reduces Labor & Maintenance Costs**



...setting performance
standards worldwide...

APPLICATIONS

SLIP-NOT is ideal for schools, apartment buildings, nursing homes, hospitals, hotels/motels, office complexes, restaurants, warehouses and any other heavy foot traffic areas. It's excellent for use on stairways and steps, hallways, walkways and most other hard surfaces.

DIRECTIONS

Surface Preparation: The surface should be dry, clean and free of oil, wax, dirt, loose paint and other contaminants. Painted surfaces should be cleaned with a mild cleaner, rinsed and dried. Before initial application to surface, a light etch or sanding is recommended. Test a small area for compatibility and adhesion. The coating is self-priming on most surfaces.

Directions For Use: Apply with ambient temperatures between 60°F and 90°F.

Shake can until ball rattles freely, then for an additional 70 seconds. Epoxy must be mixed well before and during use to achieve the correct color and texture. For best results, shake can periodically during use. Spray in a sweeping motion at a distance of 12 to 15 inches from the area being treated.

Dry Time: Dries to the touch in approximately one hour. Make sure the first coat is dry before applying the second coat. The rate of cure will vary with the film thickness, temperature and humidity. Wait 24 hours before subjecting to heavy foot traffic. Application will continue to cure for several days. Re-coat every 3 to 6 months depending on wear. The clear coating may show a slight yellowing after a period of time if in direct sunlight.

TECHNICAL DATA

Aerosol - Clear

Classification:	Epoxy coating
Flash point of Concentrate:	45°F
Flammability:	Extremely flammable aerosol
Specific Gravity:	0.8
Appearance:	Clear spray



...setting performance standards worldwide...

C-4/PC-5697/0205